



# UNITED STATES PATENT AND TRADEMARK OFFICE

UNITED STATES DEPARTMENT OF COMMERCE  
United States Patent and Trademark Office.  
Address: COMMISSIONER FOR PATENTS  
P.O. Box 1450  
Alexandria, Virginia 22313-1450  
www.uspto.gov

APPLICATION NO.	FILING DATE	FIRST NAMED INVENTOR	ATTORNEY DOCKET NO.	CONFIRMATION NO.
10/809,681	03/26/2004	Shoso Shingubara	925-287	7860
23117 7590 03/27/2007 NIXON & VANDERHYE, PC 901 NORTH GLEBE ROAD, 11TH FLOOR ARLINGTON, VA 22203			EXAMINER BAREFORD, KATHERINE A	
			ART UNIT	PAPER NUMBER
			1762	
SHORTENED STATUTORY PERIOD OF RESPONSE		MAIL DATE	DELIVERY MODE	
3 MONTHS		03/27/2007	PAPER	

**Please find below and/or attached an Office communication concerning this application or proceeding.**

If NO period for reply is specified above, the maximum statutory period will apply and will expire 6 MONTHS from the mailing date of this communication.

## Office Action Summary

Application No.

10/809,681

Applicant(s)

SHINGUBARA ET AL.

Examiner

Katherine A. Bareford

Art Unit

1762

-- The MAILING DATE of this communication appears on the cover sheet with the correspondence address --

### Period for Reply

A SHORTENED STATUTORY PERIOD FOR REPLY IS SET TO EXPIRE 3 MONTH(S) OR THIRTY (30) DAYS, WHICHEVER IS LONGER, FROM THE MAILING DATE OF THIS COMMUNICATION.

- Extensions of time may be available under the provisions of 37 CFR 1.136(a). In no event, however, may a reply be timely filed after SIX (6) MONTHS from the mailing date of this communication.
- If NO period for reply is specified above, the maximum statutory period will apply and will expire SIX (6) MONTHS from the mailing date of this communication.
- Failure to reply within the set or extended period for reply will, by statute, cause the application to become ABANDONED (35 U.S.C. § 133). Any reply received by the Office later than three months after the mailing date of this communication, even if timely filed, may reduce any earned patent term adjustment. See 37 CFR 1.704(b).

### Status

- 1) ☐ Responsive to communication(s) filed on \_\_\_\_.
- 2a) ☐ This action is **FINAL**. 2b) ☒ This action is non-final.
- 3) ☐ Since this application is in condition for allowance except for formal matters, prosecution as to the merits is closed in accordance with the practice under *Ex parte Quayle*, 1935 C.D. 11, 453 O.G. 213.

### Disposition of Claims

- 4) ☒ Claim(s) 1-7 is/are pending in the application.
- 4a) Of the above claim(s) \_\_\_\_ is/are withdrawn from consideration.
- 5) ☐ Claim(s) \_\_\_\_ is/are allowed.
- 6) ☒ Claim(s) 1-7 is/are rejected.
- 7) ☐ Claim(s) \_\_\_\_ is/are objected to.
- 8) ☐ Claim(s) \_\_\_\_ are subject to restriction and/or election requirement.

### Application Papers

- 9) ☐ The specification is objected to by the Examiner.
- 10) ☐ The drawing(s) filed on \_\_\_\_ is/are: a) ☐ accepted or b) ☐ objected to by the Examiner.  
Applicant may not request that any objection to the drawing(s) be held in abeyance. See 37 CFR 1.85(a).  
Replacement drawing sheet(s) including the correction is required if the drawing(s) is objected to. See 37 CFR 1.121(d).
- 11) ☐ The oath or declaration is objected to by the Examiner. Note the attached Office Action or form PTO-152.

### Priority under 35 U.S.C. § 119

- 12) ☒ Acknowledgment is made of a claim for foreign priority under 35 U.S.C. § 119(a)-(d) or (f).
- a) ☒ All b) ☐ Some \* c) ☐ None of:
1. ☒ Certified copies of the priority documents have been received.
2. ☐ Certified copies of the priority documents have been received in Application No. \_\_\_\_.
3. ☐ Copies of the certified copies of the priority documents have been received in this National Stage application from the International Bureau (PCT Rule 17.2(a)).

\* See the attached detailed Office action for a list of the certified copies not received.

### Attachment(s)

- 1) ☒ Notice of References Cited (PTO-892)
- 2) ☐ Notice of Draftsperson's Patent Drawing Review (PTO-948)
- 3) ☒ Information Disclosure Statement(s) (PTO/SB/08)  
Paper No(s)/Mail Date 6/04.
- 4) ☐ Interview Summary (PTO-413)  
Paper No(s)/Mail Date. \_\_\_\_.
- 5) ☐ Notice of Informal Patent Application
- 6) ☐ Other: \_\_\_\_.

## DETAILED ACTION

### *Claim Objections*

1. Claim 5 is objected to because of the following informalities: in claim 5, lines 3-4, reference to "selected from the group consisting of" is made, but only one selection is possible.

Appropriate correction is required.

### *Claim Rejections - 35 USC § 103*

2. The following is a quotation of 35 U.S.C. 103(a) which forms the basis for all obviousness rejections set forth in this Office action:

(a) A patent may not be obtained though the invention is not identically disclosed or described as set forth in section 102 of this title, if the differences between the subject matter sought to be patented and the prior art are such that the subject matter as a whole would have been obvious at the time the invention was made to a person having ordinary skill in the art to which said subject matter pertains. Patentability shall not be negated by the manner in which the invention was made.

3. This application currently names joint inventors. In considering patentability of the claims under 35 U.S.C. 103(a), the examiner presumes that the subject matter of the various claims was commonly owned at the time any inventions covered therein were made absent any evidence to the contrary. Applicant is advised of the obligation under 37 CFR 1.56 to point out the inventor and invention dates of each claim that was not commonly owned at the time a later invention was made in order for the examiner to consider the applicability of 35 U.S.C. 103(c) and potential 35 U.S.C. 102(e), (f) or (g) prior art under 35 U.S.C. 103(a).

4. Claims 1, 2, 4 and 7 are rejected under 35 U.S.C. 103(a) as being unpatentable over the admitted state of the prior art in view of Kawanoue et al (US 6229211).

The admitted state of the prior art, at pages 1-4 of the specification, teaches a known process for making embedded multilevel interconnects. For example, the process includes forming a hole portion in an insulating layer (page 2, line 25 through page 3, line 7). Then a barrier metal film of TaN is formed on the hole portion walls, by a method such as sputtering (page 3, lines 5-10). An oxide film formed on a surface of the barrier metal film is removed by etching (page 3, lines 5-15). Then, an electroless plating step of immersing the barrier metal film in a plating liquid comprising copper, thereby forming an electroless copper plating film on the barrier metal film occurs (page 3, lines 15-18).

Claim 7: Finally, an electrolytic copper plating step occurs over the electroless copper plating film (which thereby acts as the seed layer for the electrolytic plating) (page 3, lines 18-21).

The admitted state of the prior art teaches all the features of these claims except (1) the element composition ratio of N/Ta (claims 1, 2) and (2) the removal step is such that the barrier metal film is left in such a manner that it entirely covers the inner wall of the hole portion (claim 4).

However, Kawanoue teaches barrier metal films that can be used when forming embedded multilevel interconnection, where a copper layer is applied over the barrier films. Column 1, lines 5-40, column 8, lines 5-25 and Figures 3B and 3D, for example. A

barrier film is applied to a hole portion area of an insulating layer. Figures 3B and 3D, for example, and column 8, lines 5-25. The barrier film can be tantalum nitride, and can be formed by sputtering. Column 3, lines 50-65 and column 8, lines 5-25 and 50-65. The ratio of nitrogen to tantalum (N/Ta) can be 0.87, for example. Figures 3B and 3D, for example, and column 8, lines 5-25 ( film 34 or film 38). When copper is applied over the barrier film, the barrier film is provided in such a manner that it entirely covers the inner wall of the hole portion. Figures 3A and 3B and column 7, lines 45-55.

It would have been obvious to one of ordinary skill in the art at the time the invention was made to modify the admitted state of the prior art to use a N/Ta ratio of 0.87, for example, as suggested by Kawanoue with an expectation of desirable protective barrier action, because the admitted state of the prior art teaches the desire to provide TaN films by a method such as sputtering for forming barrier films for embedded multilevel interconnects, and Kawanoue teaches that TaN films provided by a method such as sputtering for forming barrier films for embedded multilevel interconnects can acceptably have a N/Ta ratio of 0.87. Furthermore, it would also have been obvious to modify the admitted state of the prior art to perform the removal step such that the barrier metal film is left in such a manner that it entirely covers the inner wall of the hole portion when copper coating is performed as suggested by Kawanoue in order to provide a desirable copper plating, because the admitted state of the prior art provides applying a barrier film to hole walls and etching the barrier film (to remove oxide) prior to applying copper and Kawanoue teaches that it is well known

Art Unit: 1762

when applying a barrier film to hole walls prior to applying copper, to have the barrier film covering all of the hole walls before when applying the copper.

5. Claim 3 is rejected under 35 U.S.C. 103(a) as being unpatentable over the admitted state of the prior art in view of Kawanoue as applied to claims 1, 2, 4 and 7 above, and further in view of Miyamoto (US 6284649).

The admitted state of the prior art in view of Kawanoue teaches all the features of this claim except that the TaN film <sup>is</sup> ~~is~~ formed by plasma nitriding tantalum.

However, Miyamoto teaches a method of forming a tantalum nitride barrier layer to use in semiconductor devices, where the barrier layer is applied in a connection hole and then Cu is applied over the barrier layer. Column 1, line 35 through column 2, line 10. Miyamoto teaches that one way to achieve the tantalum nitride barrier layer is to apply a tantalum layer and then performing plasma nitriding to form the tantalum nitride. Column 10, lines 1-55 and column 9, lines 1-30.

It would have been obvious to one of ordinary skill in the art at the time the invention was made to modify the admitted state of the prior art in view of Kawanoue to achieve the tantalum nitride barrier film by applying tantalum and plasma nitriding as suggested by Miyamoto in order to provide a desirable barrier film, because the admitted state of the prior art in view of Kawanoue teaches forming a TaN barrier film onto which copper is to be applied, and Miyamoto teaches that a well known way of achieving such a TaN barrier layer is by applying tantalum and then plasma nitriding.

6. Claims 5-6 are rejected under 35 U.S.C. 103(a) as being unpatentable over the admitted state of the prior art in view of Kawanoue as applied to claims 1, 2, 4 and 7 above, and further in view of Wang et al "Electroless Plating of Copper on Metal-Nitride Diffusion Barriers Initiated by Displacement Plating" (Hereinafter Wang Electroless Article).

The admitted state of the prior art in view of Kawanoue teaches all the features of these claims except the acid system used for the removal of oxide (claim 5) and the reducing agent for the electroless plating (claim 6). The admitted state of the prior art, page 3, lines 10-15, teaches to remove the surface of the barrier film by etching.

However, Wang Electroless Article teaches a method of forming interconnects, where tantalum nitride is used as a barrier material. Page C38. The tantalum nitride is applied to the surface by a process such as sputtering. Page C38, column 2. Then the substrate with TaN is etched with HF: HNO<sub>3</sub>:H<sub>2</sub>O solution (hydrofluoric acid: nitric acid: and water – a diluent of hydrofluoric acid). Page C38, column 2. This removes the oxide from the surface. Pages C38-C39 (see paragraph bridging pages). Then electroless copper plating is performed. Page C38, column 2. Moreover, Wang Electroless Article teaches that the reducing agent used for the electroless copper plating bath can be glyoxylic acid. Page C38, column 2.

It would have been obvious to one of ordinary skill in the art at the time the invention was made to modify the admitted state of the prior art in view of Kawanoue

Art Unit: 1762

to etch treat the tantalum nitride film by immersing in a solution of hydrofluoric acid, nitric acid, and a diluent of hydrofluoric acid to remove oxide as suggested by Wang Electroless Article in order to provide a desirable barrier film, because the admitted state of the prior art in view of Kawanoue teaches forming a TaN barrier film onto which copper is to be applied and etching before copper plating, and Wang Electroless Article teaches that a well known way of achieving such etching for a TaN barrier layer before copper plating is by applying solution treating, which would suggest immersion to apply the solution, with solution of hydrofluoric acid, nitric acid and a diluent of hydrofluoric acid to remove oxide. It would further have been obvious to modify the admitted state of the prior art in view of Kawanoue to use glyoxylic acid as the reducing agent for the copper electroless plating bath as suggested by Wang Electroless Article in order to provide a desirable copper plating, because the admitted state of the prior art in view of Kawanoue teaches forming a TaN barrier film onto which copper is applied by electroless plating, and Wang Electroless Article teaches that a well known way of achieving such electroless plating on a TaN barrier film is by using glyoxylic acid as the reducing agent for the electroless plating bath.

7. Claims 1 and 5-7 are rejected under 35 U.S.C. 103(a) as being unpatentable over the admitted state of the prior art in view of Wang et al "Suppression of native oxide growth in sputtered TaN films and its application to Cu electroless plating" (Hereinafter Wang Suppression Article).



The admitted state of the prior art, at pages 1-4 of the specification, teaches a known process for making embedded multilevel interconnects. For example, the process includes forming a hole portion in an insulating layer (page 2, line 25 through page 3, line 7). Then a barrier metal film of TaN is formed on the hole portion walls, by a method such as sputtering (page 3, lines 5-10). An oxide film formed on a surface of the barrier metal film is removed by etching (page 3, lines 5-15). Then, an electroless plating step of immersing the barrier metal film in a plating liquid comprising copper, thereby forming an electroless copper plating film on the barrier metal film occurs (page 3, lines 15-18).

Claim 7: Finally, an electrolytic copper plating step occurs over the electroless copper plating film (which thereby acts as the seed layer for the electrolytic plating) (page 3, lines 18-21).

The admitted state of the prior art teaches all the features of these claims except (1) the element composition ratio of N/Ta (claims 1), (2) the acid system used for the removal of oxide (claim 5) and (3) the reducing agent for the electroless plating (claim 6).

However, Wang Suppression Article teaches a method of forming interconnects, where tantalum nitride is used as a barrier material. Page 4697. The tantalum nitride is applied to the surface by a process such as sputtering. Page 4697, column 2. Then the substrate with TaN is etched in HF: HNO<sub>3</sub>:H<sub>2</sub>O solution (hydrofluoric acid: nitric acid: and water – a diluent of hydrofluoric acid). Page 4700, column 1. Then electroless

copper plating is performed. Page 4700, column 1. Optimum results are reached when the applied barrier film has a N/Ta ratio of 1.25. Page 4700, column 1 and page 4701, column 1. Moreover, Wang Suppression Article teaches that the reducing agent used for the electroless copper plating bath can be glyoxylic acid. Page 4698, column 1.

It would have been obvious to one of ordinary skill in the art at the time the invention was made to modify the admitted state of the prior art to use a N/Ta ratio of 1.25, for example, as suggested by Wang Suppression Article with an expectation of desirable protective barrier action, because the admitted state of the prior art teaches the desire to provide TaN films by a method such as sputtering for forming barrier films for embedded multilevel interconnects, and Wang Suppression Article teaches that TaN films provided by a method such as sputtering for forming barrier films for embedded multilevel interconnects can optimally have a N/Ta ratio of 1.25. Furthermore, it would have been obvious to modify the admitted state of the prior art to etch treat the tantalum nitride film by immersing in a solution of hydrofluoric acid, nitric acid, and a diluent of hydrofluoric acid to remove oxide as suggested by Wang Suppression Article in order to provide a desirable barrier film, because the admitted state of the prior art teaches forming a TaN barrier film onto which copper is to be applied and etching before copper plating, and Wang Suppression Article teaches that a well known way of achieving such etching for a TaN barrier layer before copper plating is etching in solution, which would suggest immersion to apply the solution, with solution of hydrofluoric acid, nitric acid and a diluent of hydrofluoric acid to remove oxide. It

Art Unit: 1762

would further have been obvious to modify the admitted state of the prior art to use glyoxylic acid as the reducing agent for the copper electroless plating bath as suggested by Wang Suppression Article in order to provide a desirable copper plating, because the admitted state of the prior art teaches forming a TaN barrier film onto which copper is applied by electroless plating, and Wang Suppression Article teaches that a well known way of achieving such electroless plating on a TaN barrier film is by using glyoxylic acid as the reducing agent for the electroless plating bath.

8. Applicant cannot rely upon the foreign priority papers to overcome this rejection using Wang Suppression Article because a translation of said papers has not been made of record in accordance with 37 CFR 1.55. See MPEP § 201.15.

9. Claim 3 is rejected under 35 U.S.C. 103(a) as being unpatentable over the admitted state of the prior art in view of Wang Suppression Article as applied to claims 1 and 5-7 above, and further in view of Miyamoto (US 6284649).

The admitted state of the prior art in view of Wang Suppression Article teaches all the features of this claim except that the TaN film <sup>is</sup> ~~is~~ formed by plasma nitriding tantalum.

However, Miyamoto teaches a method of forming a tantalum nitride barrier layer to use in semiconductor devices, where the barrier layer is applied in a connection hole and then Cu is applied over the barrier layer. Column 1, line 35 through column 2,

Art Unit: 1762

line 10. Miyamoto teaches that one way to achieve the tantalum nitride barrier layer is to apply a tantalum layer and then performing plasma nitriding to form the tantalum nitride. Column 10, lines 1-55 and column 9, lines 1-30.

It would have been obvious to one of ordinary skill in the art at the time the invention was made to modify the admitted state of the prior art in view of Wang Suppression Article to achieve the tantalum nitride barrier film by applying tantalum and plasma nitriding as suggested by Miyamoto in order to provide a desirable barrier film, because the admitted state of the prior art in view of Wang Suppression Article teaches forming a TaN barrier film onto which copper is to be applied, and Miyamoto teaches that a well known way of achieving such a TaN barrier layer is by applying tantalum and then plasma nitriding.

10. The Examiner notes that Wang Electroless Article and Wang Suppression Article were both provided by applicant with the IDS statement of June 22, 2004.

### *Conclusion*

Any inquiry concerning this communication or earlier communications from the examiner should be directed to Katherine A. Bareford whose telephone number is (571) 272-1413. The examiner can normally be reached on M-F(6:00-3:30) with the First Friday Off.


If attempts to reach the examiner by telephone are unsuccessful, the examiner's supervisor, Timothy Meeks can be reached on (571) 272-1423. The fax phone numbers

Art Unit: 1762

for the organization where this application or proceeding is assigned are (571) 273-8300 for regular communications and for After Final communications.

Other inquiries can be directed to the Tech Center 1700 telephone number at (571) 272-1700.

Furthermore, information regarding the status of an application may be obtained from the Patent Application Information Retrieval (PAIR) system. Status information for published applications may be obtained from either Private PAIR or Public PAIR. Status information for unpublished applications is available through Private PAIR only. For more information about the PAIR system, see <http://pair-direct.uspto.gov>. Should you have questions on access to the Private PAIR system, contact the Electronic Business Center (EBC) at 866-217-9197 (toll-free).

  
KATHERINE BAREFORD  
PRIMARY EXAMINER